

Perrotts is a trading name of Textiles F.R. Ltd.

Unit 4B, (30) Wharfedale Road
Euroway Trading Estate
Bradford
West Yorkshire
BD4 6SG

Textiles F.R. Limited

Flame Retardancy Finishers & Consultants

Tel: 01274 651230
Fax: 01274 651305
E-mail: sales@textilesfr.co.uk
Web site: www.textilesfr.co.uk



1413

Test Report & Certificate

UKAS TESTING LABORATORY No. 1413

British Standard Flammability Test
BS5867-2:2008:Type B

Test Document **33416 / 0**

Page 1 of 2

CUD Contract Curtain Test

Dates Tested 20/06/2023 Issued 20/06/2023

Customer Account NOB002

Order Details

NOBILIS

TFR Order No 319940

38 RUE BONAPARTE

Customer Order EMAIL OS

75006 PARIS

Order Date 09/06/2023

FRANCE

Fabric Description 11008 RAYURE PORTISSOL

Fabric Composition 100% POLYESTER FR

Quantity (metres) 1.0

Fabric Treatment Sample tested in an 'as received' state.

Cleansing Flammability testing was performed without the durability requirements stated in section 5 of BS5867-2:2008 being completed.

Filling Not applicable.

Conditioning Test specimens were conditioned in an atmosphere having a temperature of 20±2°C and relative humidity 65±5% for a minimum of 24 hours prior to testing.

Test Enclosure Conditions Temperature 20 °C Humidity 65 %


Procedure Six specimens were prepared each measuring 200± 2mm x 160± 2mm, three with the longer dimension in the length, and three with the longer dimension in the width. A butane flame was applied to each sample face for 15 seconds.

Compliance Requirements No part of any hole nor any part of the lowest boundary of any flame shall reach the upper edge or either vertical edge of any specimen, and there shall be no separation of flaming debris from any specimen.

Disclaimer This report relates only to the item tested. This test was carried out in accordance with BS EN ISO 15025 : 2002 Procedure A. The results may not apply to situations where there is a restricted air supply or prolonged exposure to large sources of heat such as in a conflagration.

Decision Rule Where statements of conformity are used in this report we will use a decision rule based on a binary simple acceptance rule, where the Acceptance limit = Tolerance limit - Expanded uncertainty at k=2 95% confidence limits (AL=TL-w, w=U (k=2)) also incorporating a guard band. The guard band will be 1mm for measurements and 1 second for timing. This rule will be used for both the inputs and outputs of the test. The maximum probability of false acceptance being less than 2.5%.

Result **PASS** Specimen complied to the requirements for BS5867-2:2008:Type B. Flammability testing was performed without the durability requirements stated in section 5 of BS5867-2:2008 being completed.



Perrotts is a trading name of Textiles F.R. Ltd.

Unit 4B, (30) Wharfedale Road
Euroway Trading Estate
Bradford
West Yorkshire
BD4 6SG

Textiles F.R. Limited

Flame Retardancy Finishers & Consultants

Tel: 01274 651230
Fax: 01274 651305
E-mail: sales@textilesfr.co.uk
Web site: www.textilesfr.co.uk



British Standard Flammability Test

BS5867-2:2008:Type B

Customer Account NOB002

NOBILIS

38 RUE BONAPARTE

75006 PARIS

FRANCE

Test Document **33416 / 0**

Page 2 of 2

CUD Contract Curtain Test

Dates Test 20/06/2023 Issued 20/06/2023

Order Details

TFR Order No 319940

Customer Order EMAIL OS

Order Date 09/06/2023

Fabric Description 11008 RAYURE PORTISSOL

Fabric Composition 100% POLYESTER FR

Quantity (metres) 1.0

Warp and Weft Observations

	Rep 1	Rep 2	Rep 3		Rep 1	Rep 2	Rep 3
Warp Flame to Edge	No	No	No	Weft Flame to Edge	No	No	No
Warp Hole to Edge	No	No	No	Weft Hole to Edge	No	No	No
Warp Flaming Debris	No	No	No	Weft Flaming Debris	No	No	No

Authorised by Kim Button
Director

Test Conducted by Ray Berry
Laboratory Technician